



## Data Sheet

Property	ASTM	Metric		Imperial	
Tensile Strength	D-638-03	MPa	50-65	psi	7,250-9,450
Modulus of Elasticity	D-638-04	MPa	2,000-3,000	psi	290,000-435,000
Elongation at Break	D-638-05	%	10-25	%	10-25
Flexural Strength	D-790-03	MPa	75-110	psi	11,000-16,000
Flexural Modulus	D-790-04	MPa	2,200-3,200	psi	320,000-465,000
Izod Notched Impact	D-256-06	J/m	20-30	ft lb/in	0.375-0.562
HDT at 0.45 MPa	D-648-06	°C	45-50	°F	113-122
Water Absorption	D570-98 24 Hr	%	1.1-1.5	%	1.1-1.5

All data provided herein, which is related to consumables, was collected from specific specimens and tests conditions and is provided for information only. Characteristics may vary if different specimens and test conditions are applied. Unless expressly provided in writing, no warranties are made and warranties of merchantability or fitness for a particular purpose are expressly disclaimed.